

ABSTRACT

A ceramic material suitable for use in production of paving tiles, construction tiles, flooring in offices, flooring in machinery plants and so forth is obtained by a method comprising steps of mixing defatted bran derived from rice bran with a thermosetting resin before kneading, subjecting a kneaded mixture thus obtained to a primary firing in an inert gas at a temperature in a range of 700 to 1000°C, pulverizing the kneaded mixture after the primary firing into carbonized powders, kneading the carbonized powders with which ceramic powders, a solvent, and a binder as desired are mixed into a plastic workpiece (kneaded mass), pressure-forming the plastic workpiece at pressure in a range of 10 to 100 MPa, and subjecting a formed plastic workpiece thus obtained again to firing in an inert gas atmosphere at a temperature in a range of 100 to 1400°C.

10073753.021102